

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : **59-197540**

(43)Date of publication of application : **09.11.1984**

---

(51)Int.Cl.

C22C 9/02

---

(21)Application number : **58-071740**

(71)Applicant : **SANPO SHINDO KOGYO KK**

(22)Date of filing : **22.04.1983**

(72)Inventor : **OZAKI YASUAKI  
OISHI KEIICHIRO**

---

### (54) COPPER BASE ALLOY

(57)Abstract:

PURPOSE: To enhance mechanical strength, elasticity, heat resistance and corrosion resistance of a copper base alloy without losing excellent processability of copper, by adding a specific amount of titanium, tin and zinc to copper.

CONSTITUTION: The composition of a copper base alloy consists of, on a wt% basis, 0.1W1.5 titanium, 0.2W2 tin, 0.05W1 zinc and the remainder of copper. As mentioned above, if titanium and tin are added together, mechanical strength, elasticity and heat resistance are remarkably enhanced. In addition by adding zinc, the oxygen amount in molten copper is reduced. This copper base alloy is availably utilized as a base material for a heat exchanger or a base material for electricity related parts.

---

### LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office